



TABELLA DI COMPATIBILITA'

A = excellent  
B = good  
C = fairly good  
D = depending on conditions  
X = not recommended  
nd = no sure data available

	AISI 316	NBR	PP	EPDM	FPM	NYL	EVA
Acetaldehyde	A	X	B	A	X	A	B
Acetamid	A	A	B	A	B	A	ND
Butyl Acetate	A	X	C	B	X	A	X
Ethyl Acetate	B	X	B	B	X	A	X
Propyl Acetato	A	X	C	B	X	C	ND
Vinyl Acetate	B	X	C	C	B	ND	ND
Acetylene	A	B	B	A	A	A	B
Vinegar	A	B	A	A	A	A	B
Acetophenone	ND	X	ND	A	X	ND	X
Acetone	A	X	A	A	X	A	X
Fatty Acids	A	B	A	X	A	B	ND
Acetic Acid	B	D	B	A	B	X	D
Acetic Acid 20%	A	B	A	A	B	X	D
Acetic Acid 80%	B	D	A	A	B	X	D
Acetic Acid Glacial	A	D	B	B	X	B	ND
Adipic Acid	A	D	C	B	B	ND	ND
Arsenic Acid	B	B	A	B	B	D	ND
Benzoic Acid	B	X	C	X	A	X	ND
Boric Acid 10%	B	A	A	A	A	B	B
Hydrobomic Acid 100%	X	X	D	A	A	X	B
Hydrobomic Acid 20%	X	X	B	A	A	X	B
Butyric Acid	C	X	C	B	C	D	D
Carbolic Acid (Phenol)	B	X	B	B	A	X	A
Carbonic Acid	A	X	A	B	A	B	A
Cyanic Acid	A	D	ND	ND	A	ND	ND
Hydrocyanic Acid 20%	A	B	A	B	A	B	ND
Citric Acid 33%	B	A	A	A	A	B	B
Chloric Acid	X	ND	ND	ND	ND	X	ND
Hydrochloric Acid 20%	X	ND	C	A	A	X	A
Hydrochloric Acid 37%	X	B	D	D	A	X	B
Chloracetic Acid	B	X	D	B	X	X	D
Chlorosulfonic Acid	B	X	X	X	X	X	ND
Cresylic Acid	A	X	B	X	A	X	ND
Cromic Acid 10%	B	X	X	D	B	X	X
Cromic Acid 30%	C	X	X	B	A	X	X
Cromic Acid 5%	A	X	X	A	A	X	X
Cromic Acid 50%	C	X	X	B	A	X	X
Fluoboric Acid	B	A	A	A	B	X	ND
Hydrofluoric Acid 100%	C	X	D	X	B	X	ND
Hydrofluoric Acid 20%	X	X	A	X	A	D	ND
Hydrofluoric Acid 50%	X	X	A	X	B	X	ND
Hydrofluoric Acid 75%	X	X	D	D	B	X	ND
Fluosilicic Acid	B	A	A	A	C	X	B
Hydrofluosilicic Acid 100%	X	B	A	A	A	X	ND
Hydrofluosilicic Acid 20%	C	A	A	A	A	X	ND
Formic Acid	B	D	B	A	D	X	ND
Phosphoric Acid (Crude)	B	X	B	B	A	C	ND
Phosphoric Acid 20%	D	X	A	B	A	C	B
Phosphoric Acid 85%	X	X	A	B	A	C	ND
Phthalic Acid	A	X	A	B	B	C	ND
Gallic Acid	B	B	A	B	A	A	B
Glycolic Acid	A	A	A	A	A	ND	ND
Hydroxyacetic Acid 70%	ND	A	ND	A	A	ND	ND
Lactic Acid	C	A	B	A	A	B	C
Linoleic Acid	A	C	C	X	C	ND	ND



TABELLA DI COMPATIBILITA'

Maleic Acid	B	X	A	X	A	A	C
Malic Acid	A	A	B	X	A	A	ND
Monochloroacetic Acid	B	X	ND	D	D	X	ND
Naphthenic Acid	ND	B	ND	X	A	ND	ND
Nitric Acid (Concentrated)	B	X	X	X	A	X	A
Nitric Acid 20%	A	X	A	B	A	X	X
Nitric Acid 50%	B	X	B	X	A	X	X
Nitric Acid 5-10%	A	X	A	B	A	X	X
Nitrous Acid	B	ND	A	A	B	ND	X
Oleic Acid	A	B	C	B	B	A	C
Acido Oxalic Acid	A	D	A	A	A	B	B
Octanoic Acid	ND	ND	ND	ND	ND	ND	ND
Palmitic Acid	B	A	C	C	B	A	B
Perchloric Acid	D	X	D	B	A	X	ND
Picric Acid	B	D	C	B	A	X	B
Pyrogallic Acid	B	ND	A	B	A	ND	ND
Cupric Acid	B	B	A	A	A	X	ND
Salicylic Acid	B	B	B	A	B	B	ND
Sulfuric Acid < 10%	B	B	A	A	A	D	B
Sulfuric Acid 10 To 75%	X	C	B	B	A	X	B
Sulfuric Acid 75 To 95%	X	D	D	C	B	X	X
Sulfuric Acid Hot & Conc.	D	X	X	X	A	X	X
Sulfuric Acid Cold & Conc.	B	X	A	D	B	X	X
Oleum 100%	A	X	X	X	A	X	ND
Oleum 25%	B	X	X	X	A	X	ND
Sulfurous Acid	B	C	A	B	A	X	B
Stearic Acid	A	B	A	B	B	A	B
Tannic Acid	A	A	A	A	A	D	ND
Tartaric Acid	D	A	A	B	A	B	B
Trichloroacetic Acid	D	ND	A	B	D	D	ND
Uric Acid	B	ND	ND	ND	ND	A	ND
White Water (Paper Mill)	A	ND	A	ND	A	A	ND
Carbonated Water	A	A	B	ND	A	A	ND
Water, Deionized	A	B	A	B	B	B	ND
Chlorine Water	D	X	X	D	A	D	ND
Sea Water	D	A	A	A	A	A	A
Distillate Water	A	A	A	A	A	B	B
Fresh Water	A	A	A	A	A	B	ND
Water, Acid, Mine	B	A	A	A	A	A	B
Turpentine (Mineral Spirit)	A	A	B	X	A	A	X
Aqua Regia (80% HCL, 20%HNO3)	X	X	C	D	B	X	X
Salt Water	B	A	A	A	A	A	B
Octyl Adipate	ND	X	ND	B	B	ND	ND
Amyl Alcohol	A	B	C	A	A	B	ND
Benzyl Alcohol	B	X	A	B	A	C	ND
Butanol	B	A	B	A	A	B	ND
Diacetone Alcohol	B	X	B	A	X	B	ND
Hexyl Alcohol	ND	A	ND	C	A	ND	X
Ethanol	A	C	A	A	A	B	C
Hexyl Alcohol	A	A	ND	D	D	A	ND
Isobutyl Alcohol	A	B	B	A	A	B	ND
Isopropyl Alcohol	B	B	A	A	A	X	ND
Methyl Alcohol	A	A	A	A	D	C	C
Octyl Alcohol	A	B	ND	A	B	A	ND
Propyl Alcohol	A	A	A	A	A	X	ND
Benzaldehyde	B	X	X	A	X	B	ND
Alums	A	A	A	B	A	A	A
Aluminum Hydroxide	D	A	A	A	A	B	ND
Aluminum Potassium Sulfate 10%	A	A	A	A	A	B	ND
Aluminum Potassium Sulfate 100%	B	A	A	A	A	X	ND
Starch	A	A	A	A	A	B	ND
Amyl Acetato	A	X	C	A	X	B	ND
Amyl Borate	ND	A	ND	X	A	ND	ND
Amyl Chloride	A	X	X	X	C	D	ND



## TABELLA DI COMPATIBILITA'

Amines	A	X	B	B	X	X	ND
Ammonia 10%	A	A	A	A	X	B	ND
Anhydrous Ammonia	A	B	A	A	C	D	ND
Liquid Ammonia	A	D	A	A	X	C	A
Ammonium Acetate	A	B	A	A	A	A	ND
Ammonium Bifluoride	C	B	A	A	A	ND	ND
Ammonium Carbonate	B	B	A	A	A	B	ND
Ammonium Chloride	B	B	A	A	A	B	ND
Ammonium Phosphate, Dibasic	D	A	A	A	A	D	A
Ammonium Phosphate, Monobasic	D	A	A	A	A	B	A
Ammonium Phosphate, Tribasic	B	A	A	A	A	B	A
Ammonium Hydroxide	B	X	A	A	B	A	ND
Ammonium Thiosulfate	A	A	ND	B	ND	ND	ND
Ammonium Nitrate	A	A	A	A	A	B	A
Ammonium Oxalate	A	X	A	A	ND	ND	ND
Ammonium Persulfate	B	A	A	B	A	X	ND
Ammonium Sulfate	B	A	A	A	A	B	A
Ammonium Sulfite	B	B	A	B	X	B	ND
Anhydrides Acetic	A	X	C	B	X	B	ND
Carbon Dioxide Dry	ND	B	ND	B	B	ND	B
Carbon Dioxide Humid	ND	B	ND	B	A	ND	B
Phosphoric Anhydride	ND	X	A	ND	ND	ND	ND
Phthalic Anhydride	A	X	X	A	A	ND	ND
Maleic Anhydride	A	X	X	X	A	ND	ND
Dry Sulfur Dioxide	ND	D	ND	A	A	ND	ND
Dry Sulfuric Dioxide	ND	X	ND	B	A	ND	X
Aniline	B	X	B	B	A	A	X
Aniline Hydrochloride	X	X	X	B	A	X	ND
Aniline Coloring	ND	X	ND	ND	B	ND	ND
Antifreeze	A	A	X	A	A	X	ND
Antimony Trichloride	X	B	A	C	A	X	ND
Rust Inhibitors	A	A	A	ND	A	ND	ND
Silver Bromide	X	ND	ND	ND	ND	ND	ND
Silver Nitrate	B	B	B	A	A	B	ND
Air	ND	A	ND	B	A	ND	A
Arochlor 1248	B	D	X	B	A	B	ND
Arsenic Trichloride	ND	A	ND	C	ND	ND	ND
Asphalt	A	B	C	X	A	A	X
Nitrogen Fertilizer	ND	ND	ND	ND	ND	ND	ND
Bath Chrome	ND	X	ND	B	A	ND	ND
Barium Carbonate	B	A	A	A	A	B	ND
Barium Cyanide	A	D	X	A	A	B	ND
Barium Chloride	B	A	A	A	A	A	ND
Barium Hydroxide	B	A	B	A	A	B	A
Barium Nitrate	B	A	A	A	A	B	ND
Barium Sulfate	C	A	C	A	A	A	B
Barium Sulfide	B	A	B	A	A	B	ND
Benzene	B	X	X	X	A	B	X
Benzene Sulfonic Acid	B	X	X	X	A	X	ND
Gasoline, Unleaded	A	B	D	X	B	A	ND
Gasoline (High-Aromatic)	A	A	A	X	A	A	X
Gasoline, Leaded, Ref.	A	A	B	X	B	A	ND
Gasoline With Sulfur Compounds	A	B	C	X	A	A	X
Gasoline Refined	A	B	C	X	A	A	X
Ethyl Benzoate	ND	X	C	ND	B	ND	ND
Oil, Ether, Naphtha	ND	A	ND	X	A	ND	X
Benzol	B	X	B	X	A	X	ND
Benzonitrile	X	ND	ND	ND	ND	ND	ND
Beer	A	A	B	A	A	B	A
Petroleum Tar	ND	B	ND	X	A	ND	X
Borax	A	B	B	A	A	A	A
Sugar Beet Broth	A	A	B	A	A	A	ND
Sugar Cane Broth	A	A	A	A	A	B	ND
Bromine	X	X	X	X	A	X	X



TABELLA DI COMPATIBILITA'

Acetyl Bromide	ND	ND	ND	ND	ND	X	ND
Lithium Bromide	ND	A	ND	A	A	ND	A
Methyl Bromide	A	C	C	X	A	C	X
Butter	A	A	ND	A	A	ND	ND
Butadiene	B	X	D	D	B	D	X
Butane	A	A	B	X	A	A	B
Butyl Amine	A	ND	C	ND	X	A	ND
Butyl Carbinol	ND	A	ND	A	A	ND	ND
Butyl Cellosolve	ND	A	ND	A	A	ND	ND
Butyl Benzoate	ND	X	ND	A	A	ND	ND
Butyl Phthalate	B	X	B	B	D	A	ND
Butyl Oleate	ND	C	ND	C	A	ND	ND
Butyl Stearate	ND	B	ND	C	A	ND	X
Butylene	A	A	ND	X	A	C	ND
Coffee	A	A	A	A	A	A	ND
Lime	A	A	ND	X	A	B	ND
Calcium Bisulfate	A	A	ND	A	ND	ND	ND
Calcium Bisulfite	A	A	A	X	A	A	B
Calcium Bisulfide	B	B	A	D	A	A	ND
Calcium Carbonate	B	A	A	A	A	A	ND
Calcium Chlorate	ND	A	ND	A	A	ND	ND
Calcium Chloride	B	A	A	A	A	B	ND
Calcium Hydroxide	B	A	A	A	C	A	A
Calcium Hypochlorite	C	D	B	C	A	X	ND
Caclium Nitrate	B	A	A	A	A	B	ND
Calcium Oxide	A	A	A	A	B	B	ND
Calcium Sulfate	B	A	A	A	A	X	ND
Carbitol	ND	C	ND	C	C	ND	ND
Carbonic Bisulfate	B	D	X	X	A	A	ND
Carbon Dioxide (Dry)	B	A	A	B	B	B	ND
Carbon Dioxide (Wet)	B	A	A	B	B	B	ND
Carbon Monoxide	A	A	A	A	A	B	ND
Carbon Tetrachloride	B	X	X	X	A	X	ND
Carbon Tetrachloride (Dry)	B	D	X	C	A	ND	ND
Carbon Tetrachloride (Wet)	A	X	X	X	ND	ND	ND
Jet Fuel	A	A	B	X	A	D	ND
Ammonium Caseinate	A	ND	ND	ND	ND	ND	ND
Tar	ND	B	ND	X	A	ND	D
Cellosolve	ND	ND	ND	B	C	ND	ND
Cellosolve Acetate	ND	C	ND	B	X	ND	ND
Ketones	A	X	D	A	X	A	ND
Cyclohexane	A	B	X	X	A	A	D
Cyclohexanone	A	X	X	B	X	A	X
Chlorine Dry	B	B	X	B	A	X	D
Chlorine Humid	D	X	X	B	A	X	C
Chloroacetone	ND	X	ND	A	X	ND	X
Chlorobenzene	B	X	D	X	A	X	X
Chloro Bromo Methane	ND	X	A	B	A	D	X
Chloroprene	ND	X	ND	X	A	ND	X
Dyphenil Chloro	ND	X	ND	X	A	ND	X
Chloroform	A	X	D	X	A	A	X
Clorox (Bleach)	A	X	X	B	A	A	ND
Acetyl Chloride	A	X	X	X	A	B	ND
Aluminum Chloride	B	A	A	A	A	C	ND
Benzoil Chloride	C	X	D	X	A	A	ND
Ethyl Chloride	A	A	X	A	A	B	ND
Ethylene Chloride	B	X	D	X	B	A	X
Ferric Chloride	X	A	A	A	A	A	A
Mercuric Chloride	X	A	B	B	A	X	B
Chloromethane	B	X	C	C	B	D	X
Methylene Chloride	ND	X	ND	C	B	ND	X
Sulfuryl Chloride	ND	ND	ND	ND	ND	ND	ND
Thionyl Chloride	ND	X	ND	C	B	ND	X
Vinyl Chloride	B	X	ND	D	B	B	X



TABELLA DI COMPATIBILITA'

Vinylidene Chloride	ND	C	ND	X	B	ND	X
Ferrous Chloride	X	A	A	ND	A	X	ND
Stannic Chloride	X	A	A	A	A	C	ND
Stannous Chloride	A	A	A	D	A	D	B
Glue	B	A	ND	A	B	B	A
Cresol	A	X	X	X	A	X	ND
Creson	ND	B	ND	X	A	ND	ND
Crotonaldehyde	ND	A	ND	A	A	ND	ND
Decalin	ND	X	ND	X	A	ND	X
Dichloro Benzene	C	X	D	X	D	X	ND
Dichloroethane	B	X	X	ND	D	B	ND
Dichloro Isopropyl Ether	ND	X	ND	C	C	ND	X
Diesel Fuel	B	A	B	X	A	A	D
Diethanolamine	ND	C	ND	A	ND	ND	ND
Diethylamine	A	D	B	B	A	A	C
Diethylene Glycol	A	A	A	A	A	B	A
Diphenyl	B	X	X	X	A	ND	X
Diphenyl Oxide	A	A	X	X	A	ND	
Diisobutylene	ND	B	ND	X	A	ND	X
Diisopropyl Benzene	ND	X	ND	X	A	ND	X
Diisopropyl Ketone	ND	X	ND	B	X	ND	X
Dimethylamine	B	X	X	B	X	A	ND
N,N-Dimethylaniline	B	X	X	B	X	A	X
N,N-Dimethylformamide	B	X	A	B	D	A	ND
1,4-Dioxane	ND	X	ND	B	X	ND	ND
Diethyl Phtalate	ND	C	ND	B	A	ND	ND
Diethyl Sebacate	ND	X	ND	B	A	ND	ND
Weed Killers	A	A	ND	ND	A	A	ND
Dowtherm A	ND	X	ND	X	A	ND	X
Dowtherm E	ND	X	ND	X	B	ND	X
Helium	ND	A	ND	A	A	ND	A
Epichlorohydrin	ND	X	ND	B	X	ND	ND
Hexaldehyde	ND	X	ND	A	X	ND	B
Hexane	A	A	C	X	A	B	C
Hexene	ND	B	ND	X	A	ND	C
Ethane	B	A	X	X	A	X	C
Ethanolamine	A	B	X	B	X	A	ND
Ether	A	X	X	X	X	A	X
Butyl Ether	B	B	X	X	X	A	ND
Benzyl Ether	ND	X	ND	B	ND	ND	ND
Diethyl Ether	B	X	B	X	X	B	ND
Isopropyl Ether	A	B	B	X	X	B	ND
Ethyl Cellosolve	ND	X	ND	B	X	ND	ND
Ethyl Cellulose	ND	B	ND	B	X	ND	ND
Ethyl Ether	B	X	X	X	X	B	ND
Ethyl Sulfate	X	A	ND	ND	A	ND	ND
Ethylene Chlorohydrin	B	X	X	B	A	X	ND
Ethylenediamine	B	A	ND	A	B	X	B
Ethylene	ND	A	ND	X	A		C
Ethylene Dichloride	B	D	D	D	A	B	ND
Ethylene Bromide	A	X	X	D	A	ND	ND
Ethylene Oxide	B	X	X	C	X	B	ND
Ethyl Mercaptan	ND	X	ND	X	B	ND	ND
Phenylhydrazine	ND	X	ND	B	A	ND	ND
Phenol 10%	B	X	C	B	A	X	X
Ferric Nitrate	B	A	A	A	A	A	ND
Ferric Sulfate	A	A	A	A	A	B	A
Aluminum Fluoride	X	A	A	A	A	B	ND
Stannic Fluoborate	A	A	ND	ND	A	ND	ND
Fluorine	A	X	X	B	D	X	ND
Fluorobenzene	ND	X	ND	X	A	ND	X
Fluorine	ND	X	ND	X	B	ND	X
Sewage	ND	A	ND	C	A	ND	ND
Formaldehyde 100%	A	D	D	A	X	X	B



TABELLA DI COMPATIBILITA'

Formaldehyde 40%	A	B	A	A	A	A	B
Sodium Phosphate Dibasic	B	A	A	A	A	B	A
Sodium Phosphate Monobasic	B	A	A	A	A	B	A
Sodium Phosphate Threebasic	B	A	A	A	A	A	A
Phosphorus	A	ND	A	ND	ND	ND	ND
Phosphorus Trichloride	A	X	ND	B	B	ND	ND
Freon 11	A	B	A	X	B	X	ND
Freon 12	B	A	A	B	B	B	ND
Freon 22	A	X	B	A	X	B	ND
Freon TF	A	A	X	X	B	X	ND
Furfurol	B	X	X	X	X	B	ND
Blast-Furnace Gas	ND	C	ND	C	A	ND	C
Coke-Oven Gas	ND	C	ND	C	A	ND	C
Natural Gas	A	A	A	X	A	ND	ND
Gelatin	A	A	A	A	A	B	A
Glycerin	A	A	A	A	A	B	A
Glycol	B	A	A	A	A	A	A
Glucose	A	A	A	A	A	A	A
Shellac (Orange)	A	A	A	A	A	B	ND
Shellac (Bleached)	A	A	A	A	A	B	ND
Grease	A	A	ND	X	A	ND	ND
Sodium Hydroxide 20%	B	A	A	B	D	A	C
Sodium Hydroxide 50%	C	B	A	C	X	A	C
Sodium Hydroxide 80%	C	X	A	C	X	D	C
Hydrazine	A	B	D	A	A	ND	ND
Aromatic Hydrocarbons	D	X	X	X	A	ND	ND
Hydroquinone	B	X	A	X	B	X	ND
Hydrogen (Gas)	A	A	A	A	A	A	ND
Hydrogen Peroxide 10%	B	X	A	A	A	D	ND
Hydrogen Peroxide 100%	A	X	C	X	A	X	ND
Hydrogen Sulfide Dry	A	X	B	B	X	D	ND
Hydrogen Sulfide Wet	A	X	B	B	X	D	ND
Ammonium Hydroxide 10%	ND	B	ND	A	B	ND	B
Ammonium Hydroxide Conc	ND	B	ND	A	B	ND	B
Potassium Hydroxide	B	C	A	A	B	D	C
Ink	D	A	ND	ND	A	D	ND
Iodine	X	B	D	B	A	A	ND
Iodine (In Alcohol)	ND	ND	ND	A	ND	D	ND
Iodoform	A	X	ND	A	ND	ND	ND
Isotane	ND	A	X	ND	A	X	ND
Iso-Octane	B	A	A	X	B	B	C
Iso-Octane 50% -Toluene 50%	ND	B	ND	X	A	ND	X
Iso-Octane 70% -Toluene 30%	ND	B	ND	X	A	ND	D
Kerosene	A	A	B	X	A	A	D
Ketchup	A	A	A	A	A	A	ND
Lacquers	A	X	X	X	X	B	ND
Lard	A	A	C	X	A	B	ND
Butyl Lactate	ND	B	ND	ND	ND	ND	ND
Ethyl Lactate	ND	B	ND	ND	ND	ND	ND
Milk	A	B	B	A	A	A	A
Latex	A	A	A	A	A	B	ND
Ligroin (Petroleum Ether Or Benzine)	A	A	A	X	A	X	ND
White Liwuor (Pulp Mill)	A	A	B	ND	A	B	ND
Lithium Chloride	A	A	A	B	B	ND	ND
Lithium Hydroxide	B	D	ND	ND	ND	ND	ND
Lubricants	A	A	B	X	A	B	ND
Magnesium Bisulfate	B	B	A	ND	ND	B	ND
Magnesium Carbonate	B	A	A	A	A	ND	ND
Magnesium Chloride	X	B	B	A	B	B	B
Magnesium Hydroxide	B	A	A	A	A	C	A
Magnesium Nitrate	B	A	A	A	A	B	ND
Magnesium Oxide	A	A	ND	ND	D	ND	ND
Magnesium Sulfate	B	A	A	A	A	B	A
Mayonnaise	A	D	ND	ND	A	A	ND



TABELLA DI COMPATIBILITA'

Mash	A	A	ND	A	A	A	ND
Manganese Sulfate	B	A	ND	A	A	A	ND
Melamine	X	C	A	A	A	A	ND
Molasses	A	A	B	B	A	B	A
Menthol	ND	A	ND	A	A	ND	ND
Mercury	A	A	B	A	A	A	A
Mercuric Cyanide	D	A	B	B	B	A	ND
Mercurous Nitrate	B	C	A	B	B	ND	ND
Methane	A	A	A	X	A	A	C
Methyl Acetato	B	X	X	B	X	A	ND
Methyl Acetone	A	X	ND	B	X	A	ND
Methylamine	A	B	A	B	X	ND	ND
Methyl Dichloride	ND	X	X	X	B	D	ND
Methyl Isobutyl Ketone	B	X	A	C	X	B	ND
Methyl Isopropil Ketone	A	X	ND	D	X	A	ND
Methyl Acrylate	ND	X	X	B	X	ND	ND
Methyl Butyl Ketone	A	X	X	B	X	X	X
Methyl Cyclopentane	ND	ND	ND	X	B	ND	ND
Methyl Alcohol 10%	A	A	A	A	D	C	ND
Methyl Cellosolve	B	B	B	B	X	D	ND
Methyl Chloride	A	X	X	X	B	C	ND
Methyl Oleate	ND	X	ND	B	B	ND	ND
Methyl Ethyl Ketone	A	X	B	A	X	B	X
MEK Peroxide	ND	X	ND	X	X	ND	ND
Methyl Methacrylate	B	X	X	X	X	ND	ND
Methyl Salicylate	ND	X	ND	B	ND	ND	ND
Honey	A	A	A	A	A	A	ND
Monochloro Benzene	ND	X	ND	X	B	ND	X
Monoethanol Amine	A	C	B	B	X	A	ND
Monomethyl Aniline	ND	X	ND	ND	B	ND	X
Carbon Monoxide	ND	B	ND	B	A	ND	ND
Morpholina	B	X	B	X	ND	A	ND
Mustard	A	B	A	A	X	A	ND
Grape Juice	A	A	ND	A	A	A	ND
Naphtha	A	A	B	X	A	A	ND
Naphtalene	A	X	B	X	A	B	X
Nickel Chloride	D	B	A	B	B	D	B
Nickel Nitrate	B	B	A	A	A	B	ND
Nickel Sulfate	C	B	A	B	A	B	A
Aluminium Nitrate	A	B	B	B	B	B	ND
Propyl Nitrate	ND	X	ND	B	X	ND	ND
Sodium Nitrate	C	B	A	A	A	B	ND
Acrylonitrile	B	X	B	X	X	B	ND
Ammonium Nitrite	A	D	A	A	X	X	A
Nitrobenzene	B	X	C	C	B	C	ND
Nitro Ethane	ND	X	ND	B	X	ND	ND
Nitro Methane	B	X	B	B	X	C	ND
Oleum	ND	C	ND	B	B	ND	X
ASTM Oil, No.1	A	A	B	X	A	A	B
ASTM Oil, No.2	A	A	B	X	A	A	C
ASTM Oil, No.3	A	A	B	X	A	A	D
Fuel Oil, Light	A	A	A	X	A	B	ND
Bay Oil	A	ND	ND	ND	A	ND	ND
Anise Oil	A	ND	ND	ND	ND	ND	ND
Aniline Oil	A	X	A	B	D	A	ND
Peanut Oil	A	A	D	D	A	ND	C
Orange Oil	A	A	A	ND	A	ND	ND
Cinnamon Oil	A	ND	X	ND	A	ND	ND
Coconut Oil	A	A	B	X	A	ND	C
Tanning Oil	A	A	ND	ND	A	ND	ND
Creosote Oil	B	X	D	X	A	X	ND
Cod Liver Oil	A	A	B	A	A	ND	ND
Clove Oil	A	A	ND	ND	A	ND	ND
Lemon Oil	A	ND	ND	X	A	ND	ND



TABELLA DI COMPATIBILITA'

Linseed Oil	A	A	A	D	A	B	C
Corn Oil	A	X	A	D	B	A	ND
Peppermint Oil	A	X	ND	ND	A	ND	ND
Olive Oil	A	X	A	X	A	B	B
Palm Oil	A	A	ND	A	A	ND	ND
Pine Oil	A	X	B	X	A	A	X
Rapeseed Oil	A	X	X	A	A	A	ND
Rosin Oil	A	X	X	A	A	ND	ND
Castor Oil	A	B	A	B	A	A	ND
Cotton Seed Oil	A	A	A	X	A	B	C
Sesame Seed Oil	A	A	A	ND	A	ND	ND
Silicone Oil	A	A	A	A	A	B	A
Soyabean Oil	A	A	B	D	A	A	C
Sperm Oil (Whale)	A	A	ND	ND	A	ND	ND
Ginger Oil	X	A	ND	A	A	ND	ND
Hydraulic Oil ( Petro)	A	A	X	X	A	B	ND
Hydraulic Oil (Synthetic)	A	X	X	A	A	B	ND
Mineral Oil	A	A	A	X	A	A	C
Motor Oil	A	A	B	X	ND	A	ND
Transformer Oil	A	A	B	X	A	B	ND
Turbine Oil	A	B	C	A	A	A	ND
Gold Monocyanide	A	A	ND	ND	A	ND	ND
Ortho-Dichloro Benzene	ND	X	ND	X	B	ND	X
Diphenyl Oxides	ND	X	ND	X	A	ND	X
Mesityl Oxides	ND	X	ND	C	X	ND	ND
Propylene Oxide	ND	X	ND	B	X	ND	ND
Nitrous Oxide	B	ND	X	A	B	D	ND
Oxygen	ND	B	ND	A	A	ND	A
Ozone	A	X	B	A	A	X	A
Cream	A	A	A	A	A	A	ND
Para-Dichloro Benzene	ND	ND	ND	X	B	ND	X
Paraffin	A	B	B	X	B	B	ND
N-Pentane	D	A	X	X	A	B	C
Sodium Perborate	B	B	A	A	A	C	ND
Perchloroethylene	B	D	X	X	A	D	ND
Sodium Peroxite	A	B	B	A	A	B	A
Petroleum	B	A	C	X	A	B	C
Pinene	ND	B	ND	X	A	ND	X
Lead Acetate	C	B	B	A	X	A	B
Lead Nitrate	C	A	A	A	A	ND	ND
Lead Sulfamate	D	B	A	A	A	C	ND
Tetraethyl Lead	ND	B	ND	ND	A	ND	ND
Pyridine	A	X	A	B	X	D	X
Vinyl Acetate (Emulsion)	ND	ND	ND	A	ND	ND	ND
Potassium Acetate, Diluted	ND	B	ND	A	X	ND	A
Potassium Bicarbonate	B	A	A	A	A	B	ND
Potassium Dichromate	C	B	A	B	A	C	ND
Potassium Bromide	B	A	A	B	A	B	ND
Potassium Carbonate	B	A	A	B	A	A	ND
Potassium Cyanide	C	B	A	B	A	B	ND
Potassium Chlorate	B	B	A	B	A	D	ND
Potassium Chloride	B	B	A	B	A	B	A
Potassium Chromate	C	B	A	A	A	B	ND
Potassium Ferricyanide	C	X	A	A	A	C	ND
Potassium Ferrocyanide	B	X	A	A	A	C	ND
Potassium Hydroxide (Lye)	B	C	A	A	B	C	ND
Potassium Iodide	B	B	A	A	A	B	ND
Potassium Hypochlorite	B	B	ND	B	ND	C	ND
Potassium Nitrate	B	A	A	A	A	C	A
Potassium Oxalate	C	ND	ND	ND	ND	ND	ND
Potassium Permanganate	B	C	B	A	A	D	ND
Potassium Sulfate	A	A	A	B	A	B	A
Potassium Sulfide	B	A	A	A	A	A	ND
Propane	A	A	A	X	A	B	C





TABELLA DI COMPATIBILITA'

Propylene	B	X	ND	X	B	ND	X
Propylene Glycol	B	A	A	A	A	A	ND
Copper Cyanide	B	A	A	A	A	X	ND
Copper Chloride	X	A	A	A	A	X	B
Copper Fluoborate	X	B	ND	ND	A	ND	ND
Copper Nitrate	A	A	A	ND	A	X	ND
Cuprous Sulfate	B	A	A	A	A	X	A
Brewery Slop	A	A	ND	ND	A	ND	ND
Furan Resin	A	X	X	D	X	ND	ND
Rosins	B	A	A	ND	A	B	ND
Resorcinal	N	ND	A	C	B	X	ND
Rum	A	A	A	A	A	A	ND
Arsenic Salts	N	ND	ND	ND	A	A	ND
Chromium Salts	ND	ND	ND	ND	ND	B	ND
Tin Salts	X	A	A	B	A	ND	ND
Tomato Juice	A	A	A	A	A	B	ND
Soy Sauce	A	A	ND	ND	A	A	ND
Salad Dressings	A	A	A	ND	A	A	ND
Soap Solution	B	A	A	A	A	B	ND
Chocolate Syrup	A	A	A	A	A	A	ND
Tallow	A	A	A	A	A	B	ND
Cider	A	A	A	A	A	A	ND
Buttermilk	A	A	B	B	A	C	ND
Whey	A	A	ND	ND	A	ND	ND
Ethyl Silicate	ND	A	ND	A	A	ND	ND
Sodium Silicate	B	A	A	A	A	B	A
Silicone	A	A	A	A	A	B	ND
Skydrol 500	ND	X	ND	A	X	ND	ND
Skydrol 7000	ND	X	ND	A	X	ND	ND
Sodium Acetato	C	B	A	A	X	C	ND
Sodium Alluminate	A	A	ND	A	A	B	ND
Sodium Benzoate	ND	B	A	A	B	C	ND
Sodium Bicarbonate	B	B	A	A	A	A	B
Sodium Bisulfate	D	B	A	A	A	D	B
Sodium Bisulfite	C	A	A	A	A	D	ND
Sodium Bromide	D	ND	ND	A	B	C	ND
Sodium Carbonate	A	B	A	A	A	B	A
Sodium Cyanide	C	A	A	A	A	B	ND
Sodium Chlorate	C	B	A	A	A	X	ND
Sodium Chloride	B	A	A	A	A	B	A
Sodium Chromate	B	A	ND	ND	A	D	ND
Sodium Ferrocyanide	B	A	A	A	A	ND	ND
Sodium Fluoride	X	B	A	A	A	B	ND
Sodium Hydrosulfite	ND	D	ND	B	A	A	ND
Sodium Hypochlorite 10%	D	B	A	B	B	X	ND
Sodium Hypochlorite 100%	X	X	B	C	B	X	ND
Sodium Hyposulfate	A	ND	ND	ND	ND	ND	ND
Sodium Metaphosphate	A	A	B	A	A	B	ND
Sodium Metasilicate	A	A	A	B	A	A	ND
Sodium Sulfate	C	A	A	A	A	A	A
Sodium Sulfite	A	A	A	A	A	X	B
Sodium Sulfide	X	A	A	A	A	B	ND
Sodium Thiosulfate	B	B	A	A	A	B	A
Aluminum Sulfate	B	A	A	A	A	A	A
Ferrous Sulfate	B	A	A	A	B	X	ND
Carbon Disulfide	ND	X	ND	X	A	ND	X
Tanning Liquors	A	C	B	B	A	B	ND
Soap Solution	ND	A	ND	A	A	ND	A
Photographic Solutions	ND	B	A	B	C	B	ND
Bleaching Liquors	ND	X	B	A	A	D	ND
Acetate Solvent	A	D	C	A	X	A	ND
Stoddard Solvent	A	A	D	X	A	A	ND
Dry Solvents With A Chlorine Base	ND	X	ND	X	C	ND	X
Lacquer Thinners	A	X	X	X	X	B	X



TABELLA DI COMPATIBILITA'

Sorghum	A	A	ND	ND	A	A	ND
Stearin	ND	B	ND	B	A	ND	C
Styrene	A	X	ND	X	B	B	X
Cane Juice	A	A	D	A	A	A	ND
Fruit Juice	A	A	B	ND	A	A	ND
Vegetable Juice	A	A	ND	A	A	A	ND
Photographic Developer	A	A	A	B	A	ND	ND
Tannic Acid	ND	A	ND	A	A	ND	A
Terpineol	ND	B	ND	C	A	ND	X
Tetrabromo Ethane	ND	X	ND	X	A	ND	X
Tetrachloro Ethane	A	X	C	X	A	D	X
Tetrachloro Ethylene	A	X	X	X	A	B	X
Carbon Tetrachloride	ND	C	ND	X	A	ND	X
Tetrahydrofuran	A	X	D	X	X	A	X
Tetralin	ND	D	ND	X	A	ND	X
Tetrabutyl Titanate	ND	B	ND	A	A	ND	ND
Titanium Tetrachloride	ND	C	ND	X	A	ND	X
Toluene	A	X	D	X	D	X	X
Varnish	A	B	A	X	A	A	ND
Strasbourg Turpentine	A	ND	X	X	A	B	ND
Triacetin	ND	B	ND	A	X	ND	ND
Tributyl Phosphate	ND	B	ND	A	X	ND	ND
Tributyl Mercaptan	ND	X	ND	X	A	ND	X
Tributoxyethyl Phosphate	ND	X	ND	B	A	ND	ND
Trichloroethane	B	X	D	X	A	D	ND
Trichloroethylene	B	X	D	X	A	D	X
Trichloropropane	A	X	ND	ND	A	ND	ND
Tricresyl Phosphate	B	X	B	A	A	A	ND
Triethanol Amine	ND	C	ND	B	X	ND	ND
Triethyl Amine	A	D	X	A	X	B	D
Trinitro Toluene	ND	X	ND	X	B	ND	ND
Trioctyl Phosphate	ND	X	ND	A	B	ND	ND
Urea	B	B	A	A	A	A	A
Urine	A	B	A	B	B	B	ND
Steam: At Min. Temperature Of 150°C	ND	C	ND	B	C	ND	C
Saturated Ammonia Hot	ND	A	ND	A	X	ND	D
Saturated Ammonia Cold	ND	B	ND	X	X	ND	ND
Petrolatum	A	A	X	A	A	B	ND
Wine And Whisky	A	A	A	A	A	B	B
Xylidenes	ND	C	ND	C	X	ND	X
Xylene	B	X	B	X	B	A	X
Zinc Acetate (Water Solution)	ND	B	ND	A	X	ND	ND
Zinc Chloride	B	A	A	A	A	A	B
Zinc Hydrosulfite	A	A	ND	A	ND	A	ND
Zinc Sulfate	A	A	A	A	A	A	B
Sulfur Dioxide	B	X	B	A	A	D	ND
Sulfur Chloride	X	X	D	X	A	B	ND
Sulfur Hexafluoride	ND	B	ND	B	ND	B	ND
Sulfur Trioxide (Dry)	A	X	X	D	A	B	ND