

NORDVLIES

HYGIENE

WIPEX® SOFT & WORK

Technisches Datenblatt

Physical Properties	Target	Minimum	Maximum	Test Method
Weight (gsm)**	85,0	80,0	90,0	ASTM 1117
Caliper (.001", 1 ply)	29,0	26,5	31,5	ASTM 1117
Tensile Dry MD (N/m)	600,0			ASTM 1117
Tensile Dry CD (N/m)	405,0	270,0		ASTM 1117
Tensile Wet CD (N/m)	250,0	174,0		ASTM 1117
Water Capacity (g/4"x4")	6,0	5,5		ASTM 1117
Absorbtion Rate (sec. 1 ply)	2,0		<2,5	ASTM 1117
MD Stretch (%)	30,0			ASTM 1117

** Weight is based an aream equal to 500 sheets measuring 2'x 3' or 3000 sq. Feet.