

Eigenschaften der Bio Materialien

Bio-Material	Temperatur-Beständigkeit		Backofen	Einfrieren	Fett	Flüssigkeiten	Zertifiziert gemäß EN 13432
	min.	max.					
Holz	-18 ° C	70 ° C	-	✓	-	-	-
Papier	-25 ° C	85 ° C	-	✓	✓	✓	-
Palmblatt	-25 ° C	220 ° C	✓	✓	✓	✓	✓
Bambus	-5 ° C	40 ° C	-	-	-	-	-
Zuckerrohr	-25 ° C	220 ° C	-	✓	✓	✓	✓
PLA	0 ° C	40 ° C	-	-	✓	✓	✓
C-PLA	-5 ° C	90 ° C	-	-	✓	✓	✓